



Lion Elastomers LLC

36191 Highway 30 • Geismar, LA 70734  
800 / 535-9960 • www.lionelastomers.com

## Trilene<sup>®</sup> 65 Liquid Polymer

## Product Data

An Ethylene-Propylene-Dicyclopentadiene Liquid Polymer

### Typical Properties

|  |             |
|--|-------------|
| Color  | Pale Yellow |
| Ash  | <0.1%       |
| Volatiles at 100°C (212°F)                               | <0.5%       |
| Specific Gravity   | 0.86        |
| Molecular Weight, Da<br>(GPC)                            | 47,000      |
| Brookfield Viscosity<br>(cps, RVT #7)<br>at 60°C (140°F) | 1,900,000   |
| at 100°C (212°F)   | 177,000     |
| Degree of Unsaturation<br>% Diene                        | 10.0        |
| Type   | DCPD        |
| Ethylene/Propylene                                       | 50/50       |

04/16  
Trilene65

**Notice:** All information supplied by or on behalf of Lion Elastomers LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.