



Lion Elastomers LLC

36191 Highway 30 • Geismar, LA 70734
800 / 535-9960 • www.lionelastomers.com

Trilene[®] CP1100 Liquid Polymer

Product Data

An Ethylene-Propylene Liquid Copolymer

Typical Properties

Color	Pale Yellow
Ash	<0.1%
Volatiles at 100°C (212°F)	<0.5%
Specific Gravity	0.86
Molecular Weight, Da (GPC)	6,400
Brookfield Viscosity (cps, RVT #7)	
at 60°C (140°F)	19,000
at 100°C (212°F)	1,000
Degree of Unsaturation	None
Ethylene/Propylene	43/57

04/16

TrileneCP1100-LETrileneCP1100

Notice: All information supplied by or on behalf of Lion Elastomers LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.